



TECHNICAL DATA SHEET

TACKY FLUX BTFO-81-1

ROLO Tacky Flux (WEE/RoHS conformant)

Type 1.2.3.1 acc. UNE-EN ISO 9454:2016 // ROLO acc. J-STD-004

TECHNICAL DATA	
Flux type	No clean tacky flux (ROLO)
Appearance	Clear yellow/white gel
Odor	Mild odor
Density at 20°C (gcm ⁻³)	0.9-1.0
Activators/resin	Modified rosins, mixed carboxylic acids
Durability	24 months
Packaging	10 ml syringe

GENERAL INFORMATION:

The soldering tacky flux, **BTFO-81-1**, has been specially developed for repair soldering, reflow applications and direct chip attach applications, and is suitable for dip tinning as well as special applications. **BTFO-81-1** is characterized by enhanced wetting and spreading properties.

Application takes place via a dosing syringe with a metallic tip. This enables an accurate dosing and positioning of the flux. The processing of the soldering tacky flux can be done with the aid of hot air or soldering irons.

The residue left is clear, non-corrosive and non-conductive so there is no need to remove it, but it can be easily cleaned with isopropanol, solvent, or semi-aqueous systems. **BTFO-81-1** is compatible with both leaded and lead-free applications.

CUSTOMER ADDED VALUE:

- Very good desoldering & soldering properties (capillarity, wetting).
- Broad process window.
- Exact dosage.
- VOC-free.
- Clear, non-conductive, non-corrosive post-process residue.

Last revision: 13/01/2023



TECHNICAL DATA SHEET

TACKY FLUX BTFO-81-1

STORAGE AND HANDLING

- Protect from sunlight.
- Keep container tightly closed.
- Do not handle until all safety precautions have been read and understood.
- Minimum storage temperature: 5°C, do not freeze.
- Maximum storage temperature: 25°C.
- Allow the flux to reach ambient temperature before use.

ADDITIONAL RECOMMENDATIONS

Dosing needles need care, with longer operating interrupts. The gels could dry, and the needles start blocking. This can be avoided if the needle is removed and rinsed with isopropanol or a cleaning gel. This will not affect the soldering results since the remainders of the cleaning gel/isopropanol will evaporate during the soldering process with the solvent system of the flux gel.

FORMATS

Name	Flux	Weight/Packaging
TACKY FLUX BTFO-81-1	ROLO	10 ml syringe - Unit Packaging: 40 units



Includes plunger
and metal
needle for its
application.

Last revision: 13/01/2023